



PACTOTile GP-C

Economical General Purpose Tile Adhesive

DESCRIPTION

PACTOTile GP-C is white / grey cement based polymer modified adhesive powder to which water is added before application. It is composed of selected binders, graded fillers and other additives.

TYPICAL USES

PACTOTile GP-C is an economical good quality adhesive for permanent fixing of ceramic floor and wall tiles for mostly interior applications, but can be used as well for moderate external applications. It can also be used for fixing light weight claddings.



STANDARD COMPLIANCE

BS 5980 Type 1 Class A

ADVANTAGES

- Extended open / wet time
- High adhesive bond strength
- Ready for use just add water
- Good slip resistance

PACKAGING

25 kg. bag

PROPERTIES

Appearance	Powder
Color	White / Grey
Mixing ratio	4.5 lit/25 kg
Density (Wet)	1.7 kg/lit
Approx. coverage	5m ² /25 kg @ 3 mm thickness
Working time	Approx. 45 mins.
Bond Strength	> 0.5 N/mm ² @ 28 days

APPLICATION INSTRUCTION

Surface Preparation

The surfaces must be sound, clean, dimensionally stable and free from all traces of oil, grease, paint, mould release agent and curing compound. The surface should be damped a few hours before application of PACTOTile GP-C.

MIXING

Add 4-5 liters of clean water for each 25 kg bag of PACTOTile GP-C. Mix until a uniform, lump free consistency is achieved. Leave the mix to stand for 10 minutes, and then stir it before using a slowspeed, hand held electric drill with a suitable paddle can be used.

APPLICATION

PACTOTile GP-C should be spread on the surface to a uniform thickness of 3-4 mm, and then combed horizontally. Place tile firmly into adhesive bed ensuring good contact with a twisting motion. Apply mixed PACTOTile GP-C up to a working area of not more than one square meter at a time.



JOINTS

A minimum spacing of 2 mm be left around each tile is recommended when fixing ceramic tiles.

FINISHING

Remove excess water tile adhesives with a damp cloth before material has set. Joint Grouting with PACTOTILE JT should be carried out after 24 hours.

STORAGE

Store out of direct sunlight, clear of the ground on pallets, protect from rainfall. Avoid excessive compaction. Shelf life is 12 months when stored as above.

PRECAUTIONS

As with other products containing Portland cement, the cementitious material in **PACTOTile GP-C** may cause irritation. In case of contact with eyes, immediately flush with plenty of water for at least 15 minutes. Call a physician. In case of contact with skin, wash skin thoroughly



P.O. Box no 282 676 Dubai-UAE
Tel: +971 4 885 0 886
Fax: +971 4 885 0 887
Visit us: www.pactechnologies.ae

Important Note: Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, as the conditions of any labor involved in the application is beyond our control. PAC Technologies shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use of this product. It is the responsibility of the user to ensure that the product meets his particular requirements and to use it in a suitable way. Field service, where provided, does not constitute supervisory responsibility. For additional Information contact your local PAC Technologies representative.

REV. 3 – FEBRUARY 2015